

Technical Data Sheet

Nekoosa Dye Sublimation Transfer Paper

Recommended Transfer Instructions

Material	Pressure	Temperature (°F)	Time
Metal	Medium	400	60-90 seconds
Synthetic Fabric	Light-Medium	400	45-75 seconds
Fiberboard	Medium	400	40-60 seconds
Hard Plastic	Medium	400	40-75 seconds
Ceramic Tiles	Light-Medium	400	6-10 minutes
Ceramic Mugs	Heavy	400	3-5 minutes
Mousepad	Medium	400	45-70 seconds
Glass	Medium-Heavy	400	4-7 minutes

*Please contact us for additional information on substrates not listed

*Please Note: Transfer instructions may vary depending on equipment

Drying Time:

- Faster dry time compared to competing alternatives, allowing instant transfer

Storage & Handling:

- Products should remain in protective packaging until ready for use
- Store and use product in environments with 36% to 51% relative humidity for effective printing and drying
- Allow paper to acclimate to room temperature prior to usage
- Avoid exposure to heated or air-conditioned air currents
- Avoid storing paper directly on the floor

Shelf Life:

- One-year shelf life in its original packaging. To protect the material, storing the paper in its original packaging is recommended until your next use.